


JRCure 2959 *Free Radical Type I*

Description

JRCure 2959


CAS No.: [106797-53-9] 2-hydroxy-1-[4-(2-hydroxyethoxy)phenyl]-2-methyl-1-Propanone

JRCure 2959 is a highly efficient non-yellowing radical photoinitiator for the UV curing of systems comprising of unsaturated monomers and prepolymers. It is especially recommended to use in low odor and water-borne systems, such as lacquers, printing inks and varnishes, which will be applied onto various objects, particularly paper.



Physical Properties

Appearance:	White powder	Purity:	≥99%
Melting Range:	87-91°C	Boiling Point:	331°C
Water Solubility:	7.6 g/L at 25°C	Density(20 °C)::	1.28g/cm ³



Packaging and Handling

Packaging: 20Kg/Carton 600Kg/Pallet or on request

Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless stated, proper storage will permit usage of the product for 12 months from the manufacture date. For additional handling and toxicological information, consult the Material Safety Data Sheet.